

TECHNICAL DATA

ARUDY (PALOMA, HENRI 4, STE ANNE)

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m3	NF EN 1936		2720
Porosity	%	NF EN 1936		0.1
Flexion breaking load	Mpa	NF EN 12372		19.9

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		22
Compression breaking load	Mpa	NF EN 1926		229.4
Frost resistancy	cycles	NF EN 12371		240
Slipping resistancy		NF EN 14231	wet	65

Source: CTMNC Paris

Update : juin-15