

TECHNICAL DATA

BLUE SAVOY

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m3	NF EN 1936		2740
Porosity	%	NF EN 1936		0.2
Flexion breaking load	Mpa	NF EN 12372		20.5

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		19.7
Compression breaking load	Mpa	NF EN 1926		157
Frost resistancy	cycles	NF EN 12371		240
Slipping resistancy		NF EN 14231		54
Thermal conductivity	W/(m.k)	RT 2005		3.5

Source: Quarry

Update : 01/10/2015