

TECHNICAL DATA

CHANDORE

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m ³	NF EN 1936		2670
Porosity	%	NF EN 1936		0.5
Flexion breaking load	Mpa	NF EN 12372		18.8

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		19
Absorption by capilarity	g/(m ² xS ^{0.5})	NF EN 772-11		0.3
Compression breaking load	Mpa	NF EN 772-1		207.8
Frost resistancy	cycles	NF EN 12371		240
Slipping resistancy		NF EN 14231	WET	64
Anchor tie test	N	NF EN 13364		2800

Source: QUARRY

Update : mars-15