

TECHNICAL DATA

RUOMS

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m3	NF EN 1936		2677
Porosity	%	NF EN 1936		0.3
Flexion breaking load	Mpa	NF EN 12372		8.3

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		22.3
Compression breaking load	Mpa	NF EN 1926		183.9
Frost resistancy	cycles	NF EN 12371		240
Slipping resistancy		NF EN 14231	humid	38
Anchor tie test	N	NF EN 13364	Type I	1445
		NF EN 13364	Type IIa	1531
		NF EN 13364	Type lib	1759

Source: Quarry Update : 2006

Other names : Chomerac