

**TECHNICAL DATA**

**SAINT MAXIMIN**

Roche Fine

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m <sup>3</sup>	NF EN 1936		1890
Porosity	%	NF EN 1936		29.8
Flexion breaking load	Mpa	NF EN 12372		5.2

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Absorption by capilarity	g/(m <sup>2</sup> xS <sup>0.5</sup> )	NF EN 772.11	perpendicular	278
		NF EN 772.11	parallel	239
Compression breaking load	Mpa	NF EN 772.11		20.2
Frost resistancy	cycles	NF EN 12371		<14
Anchor tie test	N	NF EN 13364	Type I	1350
		NF EN 13365	Type II a	1450
		NF EN 13366	Type II b	1400

Source: Quarry