

TECHNICAL DATA

BRETIGNY

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m3	NF EN 1936		2310
Porosity	%	NF EN 1936		14.6
Flexion breaking load	Mpa	NF EN 12372		9.8

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Compression breaking load	Mpa	NF EN 772.11		47.5
Frost resistancy	cycles	NF EN 12371		168
Anchor tie test	N	NF EN 13364	Type I	1084

Source: Quarry