

TECHNICAL DATA

STE CROIX DE MAREUIL

				Marmont	Fontenille
STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE	AVERAGE VALUE
Bulk density	kg/m ³	NF EN 1936		2608	2484
Porosity	%	NF EN 1936		2.2	6.3
Flexion breaking load	Mpa	NF EN 12372		14	8.1

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		21.5	-
Water absorption	%	NF EN 13755		0.9	2.6
Compression breaking load	Mpa	NF EN 1926		155	103
Slipping resistancy	SRV wet	NF EN 14231	polished	16	16
Anchor tie test	N	NF EN 13364		2245	1450

Source: Quarries