

TECHNICAL DATA

HAUTEVILLE

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m ³	NF EN 1936		2680
Porosity	%	NF EN 1936		0.6
Flexion breaking load	Mpa	NF EN 12372		10.9

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		20.1
Absorption by capilarity	g/(m ² xS ^{0.5})	NF EN 1925	C1	0.39
Compression breaking load	Mpa	NF EN 1926		141.8
Frost resistancy	cycles	NF EN 12371		240
Slipping resistancy	FLAMED	NF EN 14231	wet	44
	FLAMED	NF EN 14231	dry	65

Source: Quarries