

TECHNICAL DATA

SARANCOLIN OPERA FANTASTICO & GRIS VERSAILLES

STONE IDENTITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Bulk density	kg/m3	NF EN 1936		2710
Porosity	%	NF EN 1936		0.23
Flexion breaking load	Mpa	NF EN 12372		11.4

SUITABILITY	UNIT	STANDARD	COMMENTS	AVERAGE VALUE
Wear resistance	mm	NF EN 14157		24.7
Compression breaking load	Mpa	NF EN 1926		91.9
Frost resistancy	cycles	NF EN 12371		240

Source: QUARRY